



Our retail price is a recommendation only. Prices in offer may differ. All prices indicated 0,00 € will follow in the offer.

## PROMAT INSERT CCGT060204L-HP UNI35 LEFT

SKU: 4015448619178

Insert CCGT060204L-HP UNI35 left



**Categories:** [Indexable insert tools](#),  
[Interchangeable cutting inserts](#)

**Product Features:** Coating: TiN-coated

ISO designation: CCGT060204L-HP

Type: UNI35

Sense of rotation: Left

WSP: CCGT 0602

Brand: PROMAT

[Datasheet](#)

[Datasheet](#)

[Datasheet](#)

[Datasheet](#)

Scope of delivery:

10,00 ST Insert CCGT060204L-HP UNI35 left |

## PRODUCT DESCRIPTION

For a very light and soft cut for thin, long shafts and thin-walled material Further technical information:

- d: 6.35mm
- r: 0.4mm
- d1: 2.8mm
- s: 2,38mm
- l: 6,4mm
- Max. feed rate: 0.25 mm/rev in steel / 0.19 mm/rev in stainless steel / 0.25 mm/rev in cast / 0.25 mm/rev in NI metals / 0.15 mm/rev in superalloys / - mm/rev in hardened steels
- Vc max.: 260 m/min in steel / 155 m/min in stainless / 245 m/min in cast / 910 m/min in NI metals / 75 m/min in superalloys / - m/min in hardened steels
- Vc min.: 170 m/min in steel / 100 m/min in stainless / 160 m/min in cast / 255 m/min in NI metals / 30 m/min in superalloys / - m/min in hardened steels
- Min. cutting depth: 0.5 mm in steel / 0.5 mm in stainless / 0.5 mm in cast / 0.5 mm in NI metals / 0.5 mm in superalloys / - mm in hardened steels
- Max. cutting depth: 1.5 mm in steel / 1.1 mm in stainless / 1.5 mm in cast / 1.5 mm in NI metals / 0.9 mm in superalloys / - mm in hardened steels



- Min. feed rate: 0.08 mm/rev in steel / 0.08 mm/rev in stainless steel / 0.08 mm/rev in cast / 0.08 mm/rev in NI metals / 0.08 mm/rev in superalloys / - mm/rev in hardened steels

#### PRODUCT DATASHEET LEGAL NOTE

Please note that the information on this datasheet is provided without warranty and is intended only as non-binding information about the product. Any liability for damages or losses that may arise from the use of this information is excluded. We therefore recommend that you verify the information on this datasheet with other sources before making any decisions based on this information. Additional information about the product can be found on our website.